



# Wood Treated Right™

You are here: [Home](#) > [Dricon](#) > [Recommended Hardware](#)

## [Dricon® FRT Wood: Recommended Hardware](#)

Galvanized steel hardware is recommended for use with Dricon® FRT wood. Although Dricon treatment does not increase corrosion of bare or galvanized steel, the galvanizing provides an extra measure of protection of any treated wood.

### **Design Values**

Dricon FRT wood has recommended fastener design value adjustments based on full size independent testing completed at Virginia Polytechnic Institute. The adjustments for lateral and withdrawal loading of nailed, screwed and bolted joints range from 0 to 8 percent reduction.

[Overview](#)

[Product Applications](#)

[Product FAQ](#)

[Codes, Model Specs & Standards](#)

**[Recommended Hardware](#)**

[Product Literature & Videos](#)

[Licensed Producers](#)

[Product Use & Handling](#)

[Product Warranty](#)

<b>Fasteners/Connectors</b>		<b>Southern Pine</b>	<b>Douglas Fir</b>	<b>Spruce</b>	<b>Other Species</b>
Nails	Withdrawal	0.91	0.91	1.0	0.91
	Lateral	0.98	0.98	1.0	0.98
Wood Screws	Withdrawal	0.94	0.94	1.0	0.94
Bolted Joints	Parallel to Grain	0.92	0.92	1.0	0.92
	Perpendicular to Grain	0.96	0.96	1.0	0.96